

ICC-ES Evaluation Report



ESR-4133

Reissued July 2024

Subject to renewal July 2025

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2024 ICC Evaluation Service, LLC. All rights reserved.

<p>DIVISION: 06 00 00— WOOD, PLASTICS AND COMPOSITES</p> <p>Section: 06 16 00— Sheathing</p>	<p>REPORT HOLDER: WEYERHAEUSER</p>  <p>Weyerhaeuser</p>	<p>EVALUATION SUBJECT:</p> <p>DIAMOND™ FLOOR PANELS AND DIAMOND™ SHEATHING PANELS</p>	
---	--	--	---

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2021, 2018, and 2015 [International Building Code® \(IBC\)](#)
- 2021, 2018, and 2015 [International Residential Code® \(IRC\)](#)

Property evaluated:

- Structural

2.0 USES

The Diamond™ Floor Panels and Diamond™ Sheathing Panels (Diamond™ Panels) described in this evaluation report are Exposure 1 oriented strand board (OSB) products designed and manufactured for prescriptive and engineered applications.

3.0 DESCRIPTION

The Diamond™ Panels are manufactured to comply with proprietary property requirements and with performance requirements specified in the U.S. Voluntary Product Standard PS-2 as outlined in the approved quality assurance manual.

The Diamond™ Panels are manufactured with wood strands blended with the exterior type of adhesive as specified in the approved quality assurance manual. The panels are typically produced in nominal 4-foot-wide-by-8-foot-long (1219mm by 2438mm) sheets. Diamond™ Floor Panels are produced with tongue and groove along the long-edge of the panels, while Diamond™ Sheathing Panels are produced without the tongue and groove along the long-edge of the panels. Diamond™ Panels have the span rating and thickness as shown in [Table 1](#) in this evaluation report.

4.0 DESIGN AND INSTALLATION

4.1 Design:

Design capacities provided in this evaluation report supplement the design capacities prescribed in Chapter 23 of the IBC for wood structural panels. [Table 2](#) provides product design capacities for Weyerhaeuser's Diamond™ Panels. [Table 3](#) provides section properties for Weyerhaeuser's Diamond™ Panels. [Table 4](#)

provides equivalent specific gravities for the Weyerhaeuser's Diamond™ Panels for use in design of nailed connections (withdrawal and lateral) under Chapter 12 of the 2018 and 2015 ANSII/AWC *National Design Specification® for Wood Construction* (NDS).

4.2 Installation:

Diamond™ Panels must be installed in accordance with the applicable code and the manufacturer's published installation requirements.

5.0 CONDITIONS OF USE:

The DIAMOND™ Panels described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1 Panels are installed in accordance with the applicable building code, this report and supplemented by the manufacturer's installation instructions.
- 5.2 Panels are manufactured in Elkin, North Carolina, under a quality control program with inspections conducted by ICC-ES.

6.0 EVIDENCE SUBMITTED

Data in accordance with the [ICC-ES Acceptance Criteria for Wood Structural Panels \(AC182\)](#), dated April 2001, (Editorially revised April 2022).

7.0 IDENTIFICATION

- 7.1 Weyerhaeuser Diamond™ Panels are identified with a stamp that includes the product name, span rating, thickness category, exposure category, product standard, manufacturer name and address, mill number (537), date of manufacture, and evaluation report number (ESR-4133).
- 7.2 The report holder's contact information is the following:

WEYERHAEUSER
32901 WEYERHAEUSER WAY SOUTH
SUITE 102
FEDERAL WAY, WASHINGTON 98001
(888) 453-8358
www.weyerhaeuser.com
wood@weyerhaeuser.com

TABLE 1—SPAN RATING FOR DIAMOND FLOOR PANELS AND DIAMOND SHEATHING PANELS

SPAN RATING	PS-2 GRADE	PERFORMANCE CATEGORY
24 o.c.	Structural I Rated Sturd-I-Floor	23/32 inch
48/24	Structural I Rated Sheathing	23/32 inch

TABLE 2—DESIGN CAPACITIES FOR DIAMOND FLOOR PANELS AND DIAMOND SHEATHING PANELS⁽¹⁾

PERFORMANCE CATEGORY (in.)	STRENGTH AXIS ⁽²⁾	BENDING STIFFNESS EI (lbf-in ² /ft)	BENDING STRENGTH F _b S (lbf-in/ft)	PLANAR SHEAR F _s (lb/Q) (lbf/ft)	AXIAL STIFFNESS EA x10 ⁶ (lbf/ft)
23/32	Parallel	395,000	1,360	380	6.5
	Perpendicular	170,000	790	380	4.6

⁽¹⁾ Design capacities are single values that represent the allowable capacities per 1-foot of width.

⁽²⁾ Primary strength axis corresponds to the long panel dimension.

TABLE 3—SECTION PROPERTIES DIAMOND FLOOR PANELS AND DIAMOND SHEATHING PANELS⁽¹⁾

NOMINAL THICKNESS		PANEL WEIGHT (psf)	AREA A (in ² /ft)	MOMENT OF INERTIA I (in ⁴ /ft)	SECTION MODULUS S (in ³ /ft)	STATICAL MOMENT Q (in ³ /ft)	SHEAR CONSTANT lb/Q (in ² /ft)
Performance category (in.)	Average (in.)						
23/32	0.730	2.6	8.760	0.389	1.066	0.799	5.840

⁽¹⁾ Section properties represent 1-foot of width.

TABLE 4—EQUIVALENT SPECIFIC GRAVITY VALUES FOR DIAMOND FLOOR PANELS AND DIAMOND SHEATHING PANELS⁽¹⁾

PERFORMANCE CATEGORY (in.)	NAIL RESISTANCE	
	Lateral	Withdrawal
	Equivalent Specific Gravity	
23/32	0.51	0.45

⁽¹⁾ Equivalent specific gravity values are provided for use in design of nailed connections (lateral and withdrawal) in accordance with Chapter 12 of the 2018 and 2015 *National Design Specification*[®] for *Wood Construction* (NDS) (Chapter 11 of the 2012 NDS for the 2012 IBC and IRC).