

ICC-ES Evaluation Report

ESR-4322


Reissued September 2023

Revised November 2023

Subject to renewal September 2024

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2023 ICC Evaluation Service, LLC. All rights reserved.

DIVISION: 07 00 00 - THERMAL AND MOISTURE PROTECTION Section: 07 21 00—Thermal Insulation	REPORT HOLDER: HUNTSMAN BUILDING SOLUTIONS	EVALUATION SUBJECT: HUNTSMAN BUILDING SOLUTIONS LLC FOAM-LOK FL 750	
--	---	--	---

1.0 EVALUATION SCOPE

1.1 Compliance with the following codes:

- 2021, 2018 2015, 2012 and 2009 [International Building Code® \(IBC\)](#)
- 2021, 2018, 2015, 2012 and 2009 [International Residential Code® \(IRC\)](#)
- 2021, 2018, 2015, 2012 and 2009 [International Energy Conservation Code® \(IECC\)](#)
- 2013 *Abu Dhabi International Building Code (ADIBC)*[†]

[†]The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

Properties evaluated:

- Surface burning characteristics
- Physical properties
- Thermal performance (*R*-values)
- Attic and crawl space installation
- Air permeability
- Exterior walls of Types I–IV construction

1.2 Evaluation to the following green standard:

2008 ICC 700 *National Green Building Standard*[™] (ICC 700-2008)

Attributes verified:

See Section 2.0.

2.0 USES

Huntsman Building Solutions LLC Foam-Lok FL 750 is used to provide thermal insulation in buildings and to seal areas such as plumbing and conduit penetrations against air infiltration. The insulations are for use in wall cavities and floor assemblies; and in attic and crawl space installations as described in Section 4.4.

The Foam-Lok FL 750 insulation is for use in non-fire-resistance-rated construction under the IBC and dwellings under the IRC; and in Types I through IV construction when installed in accordance with Section 4.5.

The attribute of the insulation has been verified as conforming to the provisions of ICC 700-2008 Section 703.2.1.1.1(c) as an air impermeable insulation. Note that decisions on compliance for those areas rest with the user of this report. The user is advised of the project-specific provisions that may be contingent upon meeting specific conditions, and the verification of those conditions is outside the scope of this report. These codes or standards often provide supplemental information as guidance.

3.0 DESCRIPTION

3.1 Foam-Lok FL 750:

The Huntsman Building Solutions LLC Foam-Lok FL 750 foam plastic insulation is two-component, low density, open cell, spray-applied, foam plastic with a nominal density of 0.7 pcf (11 kg/m³). The polyurethane foam is produced by combining a polymeric isocyanate (A component) and proprietary resin, Foam-Lok FL 750 (B component). When stored at temperatures between 50°F (10°C) and 100°F (38°C), the components have a shelf life of twelve months.

3.2 Surface Burning Characteristics:

When tested in accordance with ASTM E84/UL 723, at a thickness of 4 inches (152 mm) and a nominal density of 0.7 pcf (11 kg/m³), Foam-Lok FL 750 has a flame spread index of 25 or less and a smoke-developed index of 450 or less. There is no thickness limit when installed behind a code-prescribed thermal barrier, except as noted in Section 4.3.2 and [Table 2](#).

3.3 Thermal Resistance:

Huntsman Building Solutions LLC Foam-Lok FL 750 has thermal resistance (*R*-values) at a mean temperature of 75°F (24°C) as shown in [Table 1](#).

3.4 Air Permeability:

Huntsman Building Solutions LLC Foam-Lok FL 750 is considered air-impermeable insulation in accordance with 2021, 2018, 2015 IBC Section 1203.3 and 2021, 2018, 2015 and 2012 IRC Sections R202 and R806.5 (2009 IRC Sections R202 and R806.4), at a minimum thickness of 2 inches (51 mm) based on testing in accordance with ASTM E2178.

3.5 Intumescent Coatings:

3.5.1 DC 315 Coating: DC 315 coating ([ESR-3702](#)), manufactured by International Fireproof Technology, International Inc. / Paint To Protect Inc., is a water-based intumescent coating supplied in 5-gallon (19L) pails and 55-gallon (208L) drums. The coating material has a shelf life of 12 months when stored in factory-sealed containers at temperatures between 50°F (10°C) and 80°F (27°C).

4.0 INSTALLATION

4.1 General:

The manufacturer's published installation instructions and this report must be strictly adhered to. A copy of these instructions and this evaluation report must be available on the jobsite at all times during installation.

4.2 Application:

4.2.1 General: Huntsman Building Solutions LLC Foam-Lok FL 750 foam plastic insulation must be applied on the jobsite using two-component, 1-to-1 ratio, spray equipment specified by Huntsman Building Solutions LLC. The foam plastic must not be sprayed onto a substrate that is wet, or covered with frost or ice, loose scales, rust, oil or grease. The foam plastic insulation must not be used in electrical outlet or junction boxes or in contact with rain or water, and must be protected from the weather during and after application. Where the insulation is used as air-impermeable insulation, such as in unvented attic spaces regulated by 2021 and 2018 IBC Section 1202.3, 2015 IBC Section 1203.3 or 2021, 2018, 2015 or 2012 IRC Section R806.5 (2009 IRC Section R806.4), the insulation must be installed at a minimum thicknesses noted in Section 3.4. The insulation can be installed in one pass to the maximum thickness. Where multiple passes are required, the cure time between passes is negligible.

The insulation may be used in areas where the maximum service temperature is no greater than 180°F (82°C). The insulation must be applied when the temperature is at or above 14°F (-10°C) and be protected from the weather during and after application.

4.3 Thermal Barrier:

4.3.1 Application with a Prescriptive Thermal Barrier: Huntsman Building Solutions LLC Foam-Lok FL 750 foam plastic insulation must be separated from the interior of the building by an approved thermal barrier, such as 1/2-inch (12.7 mm) gypsum wallboard installed using mechanical fasteners in accordance with the applicable code, or an equivalent thermal barrier complying with the applicable code. When installation is within

an attic or crawl space as described in Section 4.4, a thermal barrier is not required between the foam plastic and the attic or crawl space, but is required between the foam plastic insulation and the interior of the building. There is no thickness limit when installed behind a code-prescribed thermal barrier, except as noted in Section 4.3.2 and [Table 2](#).

4.3.2 Application without a Prescriptive Thermal Barrier or Ignition Barrier: The prescriptive 15-minute thermal barrier or ignition barrier may be omitted when installation is in accordance with the following requirements:

4.3.2.1 The insulation must be covered on all surfaces with a fire protective coating at the minimum thickness set forth in [Table 2](#).

4.3.2.2 The maximum installed thickness of the insulation must not exceed the thicknesses set forth in [Table 2](#).

4.3.2.3 The coating must be applied over the insulation in accordance with the coating manufacturer's instructions and this report.

4.4 Attics and Crawl Spaces:

4.4.1 Application with a Prescriptive Ignition Barrier: When Huntsman Building Solutions LLC Foam-Lok FL 750 is installed up to a maximum thickness of 4 inches (102 mm) within attics or crawl spaces where entry is made only for service of utilities, an ignition barrier must be installed in accordance with IBC Section 2603.4.1.6 and IRC Sections R316.5.3 and R316.5.4, as applicable. The ignition barrier must be consistent with the requirements for the type of construction required by the applicable code and must be installed in a manner so that the foam plastic insulation is not exposed. Foam-Lok FL 750 may be installed in unvented attics when the foam plastic is applied at a minimum thickness of 2 inches (51 mm) in accordance with 2021 and 2018 Section 1202.3, 2015 IBC Section 1203.3, 2021, 2018, 2015 and 2012 IRC Section R806.5 or 2009 IRC Section R806.4, as applicable.

4.4.2 Application without a Prescriptive Ignition Barrier: Where Huntsman Building Solutions Foam-Lok FL 750 insulation is installed without a prescriptive ignition barrier, in accordance with Sections 4.4.2.1, 4.4.2.2, and 4.4.2.3, the following conditions apply:

1. Entry to the attic or crawl space is to service utilities, and no storage is permitted.
2. There are no interconnected attic or crawl space areas.
3. Air in the attic or crawl space is not circulated to other parts of the building.
4. Combustion air is provided in accordance with IMC Section 701.
5. Attic ventilation is provided when required by 2021 and 2018 Section 1202.2, 2015, 2012 and 2009 IBC Section 1203.2 or IRC Section R806, except when air-impermeable insulation is permitted in unvented attics in accordance with 2021 and 2018 Section 1202.3, 2015 IBC Section 1203.3 or 2021, 2018, 2015 and 2012 IRC Section R806.5 or 2009 IRC Section R806.4, as applicable.
6. Under-floor (crawl space) ventilation is provided when required by 2021 and 2018 IBC Section 1202.4, 2015 IBC Section 1203.4 (2012 and 2009 IBC Section 1203.3) or IRC Section R408.1, as applicable.
7. If hot work is to be performed, all necessary procedures, precautions and limitations must be observed in accordance with OSHA 1926 Subpart J Standard 1926.352 requirements for hot work (welding / cutting) performed in the vicinity of combustible materials.
8. An installation certificate with the following information must be posted at each entrance:
 - Product name and installation thickness.
 - Manufacturer name, address and contact information.
 - Installation contractor name, address and contact information.
 - Attestation that the product(s) have been installed in accordance with the manufacturer's installation instructions and the requirements of the evaluation report.
 - A notice that the certificate is not to be removed or altered.
 - A list of limitations for the space including the following:
 - o Entry to the space is only to service utilities, and no storage is permitted.
 - o FIRE SAFETY WARNING: If hot work is to be performed, all necessary procedures, precautions and limitations must be observed in accordance.

4.4.2.1 Attics: In attics, Huntsman Building Solutions LLC Foam-Lok FL 750 insulation may be spray-applied to the underside of the roof sheathing and/or rafters, the underside of wood floors, and vertical surfaces, as described in this section. The thickness of the foam plastic applied to the underside of the top of the space

must not exceed 14 inches (356 mm). The thickness of the spray foam plastic insulation applied to vertical wall surfaces must not exceed 8 inches (203 mm). The foam plastic insulation must be covered on all exposed surfaces with DC315 intumescent coating at a minimum thickness of 4 wet mils (0.1 mm) [3 dry mils (0.08 mm)], applied at a rate of 0.25 gallon (0.95 L) per 100 square feet (9.2 m²). The coating must be applied over the Foam-Lok FL 750 insulation in accordance with the coating manufacturer's instructions and this report. Surfaces to be coated must be dry, clean, and free of dirt, loose debris and other substances that could interfere with adhesion of the coating. The coating is applied in one coat with low-pressure airless spray equipment.

The coating must be applied when ambient and substrate temperature is at least 60°F (16°C) and no more than 95°F (35°C). All other surfaces (including glass) must be protected against damage from the coating.

Huntsman Building Solutions LLC Foam-Lok FL 750 insulation may be installed in unvented attics when the foam plastic is applied at a minimum thickness of 2 inches (51 mm) as described in this section, in accordance with 2021 and 2018 Section 1202.3, 2015 IBC Section 1203.3, 2021, 2018 and 2015 and 2012 IRC Section R806.5 or 2009 IRC Section R806.4, as applicable.

4.4.2.2 Crawl Spaces: In crawl spaces, Foam-Lok FL 750 insulation may be spray-applied to vertical walls and the underside of floors, as described in this section. The thickness of the foam plastic applied to the underside of the floors must not exceed 14 inches (356 mm). The thickness of the spray foam plastic insulation applied to vertical wall surfaces must not exceed 8 inches (203 mm). The insulation must be covered with DC-315 coating as described in Section 4.4.2.1.

4.4.2.3 Use on Attic Floors: Foam-Lok FL 750 insulation may be installed at a maximum thickness of 13 inches (330 mm) between joists in attic floors. The insulation must be separated from the interior of the building by an approved thermal barrier. The insulation does not require an ignition barrier or a coating.

4.5 Exterior Walls in Type I, II, III and IV Construction:

4.5.1 General: Under the 2018, 2015, 2012 and 2009 IBC, when used on exterior walls of Types I, II, III or IV construction, the assembly must comply with IBC Section 2603.5 and this section, and the Foam-Lok FL 750 insulation must be installed at a maximum thickness described in [Table 3](#). The potential heat of Foam-Lok FL 750 insulation is 1963 Btu/ft² (22.1 MJ/m²) per inch of thickness when tested in accordance with NFPA 259.

4.5.2 Specific Wall Assemblies: Wall assemblies complying with Section 4.5 must be as described in [Table 3](#).

5.0 CONDITIONS OF USE:

The Huntsman Building Solutions LLC Foam-Lok FL 750 spray-applied polyurethane foam plastic insulation described in this report complies with, or is a suitable alternative to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1** This evaluation report and the manufacturer's published installation instructions, when required by the code official, must be submitted at the time of permit application.
- 5.2** The insulation must be installed in accordance with the manufacturer's published installation instructions, this evaluation report and the applicable code. If there is a conflict between the installation instructions and this report, this report governs.
- 5.3** The insulation must be separated from the interior of the building by an approved thermal barrier, except as noted in this report.
- 5.4** The insulation must not exceed the thicknesses and densities noted in this report.
- 5.5** The insulation must be protected from the weather during and after application.
- 5.6** The insulation must be applied by licensed dealers and installers certified by Huntsman Building Solutions LLC.
- 5.7** Use of the insulation in areas where the probability of termite infestation is "very heavy" must be in accordance with IRC Section R318.4 or IBC Section 2603.8, as applicable.
- 5.8** Jobsite certification and labeling of the insulation must comply with 2021, 2018, 2015 IRC Sections N1101.10.1 and N1101.10.1.1 (2012 IRC Sections N1101.12.1 and N1101.12.1.1 or 2009 IRC Sections N1101.4 and N1101.4.1) and 2021, 2018, 2015 and 2012 IECC Sections C303.1.1, C303.1.1.1, R303.1.1 and R303.1.1.1 (2009 IECC Sections 303.1.1 and 303.1.1.1), as applicable.
- 5.9** When installed in accordance with Section 4.4.2 of this report, the associated installation certificate(s) containing the required information referenced in Section 4.4.2 must be installed at each entrance to the crawlspace or attic, as applicable. The certificate(s) must be red in color and constructed of durable materials, such as metal, plastic, or laminated paper.
- 5.10** When used in unvented attics in accordance with Section 4.4.2 of this report, installation with a vapor diffusion port in accordance with 2021 IBC Section 1202.3, Item 5.2 or 2021 and 2018 IRC Section R806.5,

Item 5.2 is outside the scope of this report.

5.11 A vapor retarder must be installed in accordance with the applicable code.

5.12 Huntsman Building Solutions LLC Foam-Lok FL 750 foam plastic insulation is manufactured under a quality control program with inspections by ICC-ES.

6.0 EVIDENCE SUBMITTED

6.1 Data in accordance with the [ICC-ES Acceptance Criteria for Spray-applied Foam Plastic Insulation \(AC377\)](#), dated June 2023.

6.2 Report of tests in accordance with AC377 Appendix X.

6.3 Test report on air leakage rate in accordance with ASTM E2178.

6.4 Reports of room corner fire testing in accordance with NFPA 286.

6.5 Test report in accordance with NFPA 285, and related engineering analysis.

6.6 Report of testing in accordance with NFPA 259.

6.7 Report of fire testing in accordance with ASTM E970.

7.0 IDENTIFICATION

7.1 All packages and containers of Foam-Lok FL 750 insulation must be labeled with the Huntsman Building Solutions LLC name and address; the product name; component designation (A or B); the flame spread index and the smoke-developed index; the expiration date; and the evaluation report number (ESR-4322).

The International Fireproof Technology, Inc. / Paint To Protect Inc. DC 315 coating described in Section 3.5.1 is identified with the manufacturer's name and address, the product trade name, date of manufacture, shelf life or expiration date, the manufacturer's application instructions and the evaluation report number ([ESR-3702](#)).

7.2 The report holder's contact information is as follows:

HUNTSMAN BUILDING SOLUTIONS LLC
3315 E. DIVISION STREET
ARLINGTON, TEXAS 76011
(817) 640-4900
www.huntsmanbuilding.com

TABLE 1—THERMAL RESISTANCE (R-VALUES)

THICKNESS (inches)	R-VALUE (°F·ft ² ·h/Btu)	THICKNESS (inches)	R-VALUE (°F·ft ² ·h/Btu)	THICKNESS (inches)	R-VALUE (°F·ft ² ·h/Btu)
1	4.0	5.5	22	9.5	38
2	8.0	6	24	10	40
3	12	7	28	11.5	42
3.5	14	7.5	30	13.5	54
4	16	8	32	14	56
5	20	9	36	—	

For **S1**: 1 inch = 25.4 mm, 1°F·ft²·h/Btu = 0.176 110°K·m²/W.

¹R-values are calculated based on tested K values at 1- and 3.5-inch thicknesses.

²R-values greater than 10 are rounded to the nearest whole number.

TABLE 2—USE OF INSULATION WITHOUT A PRESCRIPTIVE THERMAL BARRIER¹

INSULATION TYPE	MAXIMUM THICKNESS (in.) (Walls & Vertical Surfaces)	MAXIMUM THICKNESS (in.) (Ceilings, Underside of Roof Sheathing/Rafters & Floors)	FIRE-PROTECTIVE COATING MINIMUM THICKNESS & TYPE (Applied to all Foam Surfaces) ²	MINIMUM THEORETICAL APPLICATION RATE OF FIRE-PROTECTIVE COATING ³	TEST SUBMITTED
FOAM-LOK FL 750	6½	11½	DC315 20 mils WFT / 13 mils DFT	1.25 gal / 100 ft²	NFPA 286

For SI: 1 inch = 25.4 mm; 1 mil = 0.0254 mm; 1 gallon = 3.38 L; 1 ft² = 0.093 m².

¹See Section 4.3.2.

²See Section 3.5.1.

³As reported in the manufacturer's application instructions. Actual application rate, based on specific project conditions, must be in accordance with the manufacturer's application instructions.

TABLE 3—NFPA 285 COMPLYING EXTERIOR WALL ASSEMBLIES^{1,2}

WALL COMPONENT	MATERIALS
Base Wall System – Use either 1, 2 or 3	1 – Concrete wall. 2 – Concrete masonry wall. 3 – Minimum 3⅝-inch-deep (92 mm), No. 20 gage, C-shaped steel studs, spaced a maximum of 24 inches on center with lateral bracing every 4 feet (1219 mm) as required by code. Sheathing shall be described in Exterior Sheathing below.
Floorline Firestopping	Minimum 4 pcf mineral wool in each stud cavity at each floorline, attached with Z-clips. Thickness must match stud cavity depth.
Cavity Insulation – Use either 1, 2, 3, 4 or 5	1 – None. 2 – Partial cavity fill with a maximum air space of 2 inches (51 mm) or full cavity depth not exceeding 7⅝ inches (194 mm) of Huntsman Building Solutions LLC Foam-Lok FL 750; MD-R-210 (ESR-3493); MD-C-200 (ESR-3199); or Proseal (ESR-3500). 3 – Any insulation qualified as noncombustible in accordance with ASTM E136. 4 – Glass fiber batt insulation ^a . 5 – Mineral fiber insulation ^a . ^a . Insulation must comply with the applicable requirements of 2018, 2015 or 2012 IBC Section 720.2 (2009 IBC Section 719.2).
Exterior Sheathing – Only for Base Wall System No.3 – Use either 1 or 2	1 – Minimum ½-inch-thick (12.7 mm), glass mat gypsum sheathing complying with ASTM C1177. 2 – Sheathing shall be attached with No. 6, 1¼-inch-long (32 mm) self-tapping screws located 8 inches (203 mm) on center along the perimeter and 12 inches (302 mm) on center in the field of wallboard. Joints must be taped and treated with joint compound in accordance with ASTM C840 or GA-216.
Exterior Insulation	Maximum thickness of 5½ inches (140 mm) of Huntsman Building Solutions LLC Proseal Eco (MD-R-210) (ESR-3493) or Proseal (ESR-3500).
Exterior Wall Covering – Use either 1, 2, 3, 4, 5, 6 or 7	1 – Brick - standard nominally 4-inch-thick (102 mm) clay brick; brick veneer anchors – standard types installed a maximum of 24 inches OC vertically on each stud ^b . 2 – Stucco - minimum ¾-inch-thick (19.1 mm), exterior cement plaster and lath with a secondary water-resistive barrier may be installed between the exterior insulation and the lath. 3 – Natural stone (limestone, granite, marble, sandstone), minimum 2-inch-thick (51 mm) ^c . 4 – Cast artificial stone, minimum 1½-inch-thick (38 mm), complying with AC51 and subject of a current ICC-ES evaluation report. 5 – Terracotta cladding, minimum of 1¼-inch-thick (32 mm) ^c . 6 – Precast concrete panels, minimum of 1½-inch-thick (32 mm) ^c . 7 – Concrete masonry units (CMU), minimum of 1½-inch-thick (38 mm) ^c . ^b . The maximum air gap between exterior insulation and cladding shall be 2 inches (51 mm). ^c . Any standard non-open-jointed installation technique such as ship-lap, etc., may be used.

¹ When used on exterior walls of Types I, II, III or IV construction, the specific wall assembly must comply with 2018, 2015, 2012, and 2009 IBC Section 2603.5.

² The exterior wall assemblies described in [Table 3](#) comply with 2018, 2015, 2012 and 2009 IBC Section 2603.5.5.