

ICC-ES Evaluation Report

ESR-4484

Reissued September 2024


This report also contains:

-FL Supplement

Subject to renewal October 2024

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2024 ICC Evaluation Service, LLC. All rights reserved.

<p>DIVISION: 07 00 00 - THERMAL AND MOISTURE PROTECTION</p> <p>Section: 07 21 00 – Thermal Insulation</p>	<p>REPORT HOLDER:</p> <p>NORTH AMERICAN SPRAY FOAM POLYMERS</p>	<p>EVALUATION SUBJECT:</p> <p>EPS 2000, Closed Cell, Spray Foam Insulation</p>	
---	---	--	---

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2018, 2015, 2012 and 2009 [International Building Code® \(IBC\)](#)
- 2018, 2015, 2012 and 2009 [International Residential Code® \(IRC\)](#)
- 2018, 2015, 2012 and 2009 [International Energy Conservation Code® \(IECC\)](#)
- 2013 Abu Dhabi International Building Code (ADIBC)†

†The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

- Other Codes (See Section 8.0)

Property evaluated:

- Surface-burning characteristics
- Physical properties
- Thermal resistance
- Attic and crawl space installation
- Air permeability
- Water vapor transmission
- Exterior walls in Types I through IV construction

1.1 Evaluation to the following green code(s) and/or standards:

- 2008 ICC 700 [National Green Building Standard™](#) (ICC 700-2008)

Attributes verified:

See Section 3.1

2.0 USES

North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation is used as a nonstructural thermal insulating material in Type VB construction (IBC) and dwellings under the IRC. The

insulation is for use in wall cavities, floor assemblies, ceiling assemblies or attics and crawl spaces when installed in accordance with Section 4.4.

Under the IRC and the 2018 and 2015 IBC, the insulation may be used as air-impermeable insulation when installed in accordance with Section 3.5.

The insulation also may be used in exterior walls of Type I, II, III or IV construction that do not exceed 40 feet (12 192 mm) in height above grade plane when used as described in Section 4.5.

3.0 DESCRIPTION

3.1 General:

North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation is a rigid, medium-density, spray-applied cellular polyurethane foam plastic insulation installed as a component of wall assemblies, ceilings, floors, crawlspaces and cavities of roofs. The foam plastic insulation is a two-component, closed-cell, one-to-one by volume spray foam system with a nominal density of 2.0 pcf (32 kg/m³). The insulation is produced in the field by combining a polymeric isocyanate (A component) with a polymeric resin blend (B component). The insulation components have a shelf life of six months when stored in factory-sealed containers at temperatures between 50°F (10°C) and 80°F (26°C).

The attributes of the insulation have been verified as conforming to the provisions of ICC 700-2008 Section 703.2.1.1.1(c) as an air impermeable insulation. Note that decisions on compliance for those areas rest with the user of this report. The user is advised of the project-specific provisions that may be contingent upon meeting specific conditions, and the verification of those conditions is outside the scope of this report. These codes or standards often provide supplemental information as guidance.

3.2 Surface-burning Characteristics:

North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation, at a maximum thickness of 4 inches (102 mm) and a nominal density of 2.0 pcf (32 kg/m³), has a flame spread index of 25 or less and a smoke-developed index of 450 or less when tested in accordance with ASTM E84 (UL 723). There are no thickness limitations when insulation is covered by a code-prescribed thermal barrier.

3.3 Thermal Resistance (R-values):

North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation has thermal resistance (R-value) at a mean temperature of 75°F (24°C), as shown in [Table 1](#).

3.4 Vapor Permeance:

EPS 2000, Closed Cell, Spray Foam Insulation has a vapor permeance of less than 1.0 perms (5.7x10⁻¹² kg/Pa-s-m²) when applied at a minimum of 1 inch (25.4 mm) thickness and may be used where a Class II vapor retarder is required by the applicable code.

3.5 Air Permeability:

EPS 2000, Closed Cell, Spray Foam Insulation foam plastic insulation, at a minimum 1-inch (25 mm) thickness, is considered air-impermeable insulation in accordance with 2018, 2015 and 2012 IRC Section R806.5 (2009 IRC Section R806.4) and 2018 IBC Section 1202.2 (2015 IBC Section 1203.3) based on testing in accordance with ASTM E283.

3.6 DC 315 Coating:

DC 315 Coating ([ESR-3702](#)), manufactured by International Fireproof Technology, Inc. / Paint to Protect Inc., is a one-component water-based coating. The coating is supplied in 5-gallon (19 L) pails and 55-gallon (208 L) drums and has a shelf life of 12 months when stored in factory-sealed containers at temperatures between 50°F (10°C) and 80°F (27°C).

3.7 Blazelok TBX Intumescent Coating:

Blazelok™ TBX intumescent coating ([ESR-3997](#)), manufactured by TPR² Corporation, is a one-component water-based liquid-applied coating. The coating is supplied in 5-gallon (19 L) pails and 55-gallon (208 L) drums and has a shelf life of 12 months when stored in factory-sealed containers at temperatures between 45°F (7°C) and 95°F (35°C).

4.0 DESIGN AND INSTALLATION

4.1 Design:

North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be installed in accordance with the manufacturer's published installation instructions and this report. A copy of the manufacturer's published installation instructions must be available at all times on the jobsite during installation.

4.2 Application:

The insulation is spray-applied on the jobsite using equipment identified in the manufacturer's published installation instructions. The North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be applied when the ambient and substrate temperature is between 50°F (10°C) and 120°F (49°C). The insulation must not be used in areas that have a maximum service temperature greater than 180°F (82°C). The foam plastic insulation must not be used in electrical outlet or junction boxes or in continuous contact with rain or water. The substrate must be free of moisture, frost or ice, loose scales, rust, oil and grease, or contaminants that will interfere with adhesion of the spray foam insulation. The North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation is applied in passes having a maximum thickness of 2 inches (51 mm) per pass. When multiple passes are required, subsequent passes can be sprayed once the core temperature drops below 100°F.

4.3 Thermal Barrier:

4.3.1 Application with a Prescriptive Thermal Barrier: North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be separated from the interior of the building by an approved thermal barrier of 1/2-inch-thick (12.7 mm) gypsum wallboard or an equivalent 15-minute thermal barrier complying with and installed in accordance with the applicable code except where the installation complies with the requirements set forth in Section 4.3.2. When installation is within an attic or crawl space as described in Section 4.4, a thermal barrier is not required between the foam plastic and the attic or crawl space, but is required between the insulation and the interior of the building.

There is no thickness limit when installed behind a code-prescribed thermal barrier except as noted in Section 4.4.2.1.

4.3.2 Application without a Prescriptive Thermal Barrier: The prescriptive 15-minute thermal barrier may be omitted when installation is in accordance with this section. The insulation and coating may be spray-applied to the interior facing of walls and the underside of roof sheathing or roof rafters, and in crawl spaces, and may be left exposed as an interior finish without a prescribed 15-minute thermal barrier or ignition barrier. The thickness of the foam plastic applied to the underside of the roof sheathing must not exceed 1 1/2 inches (292 mm). The thickness of the foam plastic applied to the vertical wall surfaces must not exceed 7 1/2 inches (191mm). The foam plastic must be covered on all surfaces with DC 315 coating at a minimum wet film thickness of 18 wet mils (0.46 mm) (12 dry mils [0.31 mm]), at a rate of 1.12 gal/100 ft² (0.457 L/m²) or with Blazelok™ TBX at a minimum wet film thickness of 18 wet mils (0.46 mm) (12 dry mils [0.31 mm]), at a rate of 1.12 gal/100 ft² (0.457 L/m²). The coating must be applied over the North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation in accordance with the coating manufacturer's instructions and this report. The DC 315 coating must be applied in accordance with the manufacturer's instructions and [ESR-3702](#). The Blazelok TBX coating must be applied in accordance with the manufacturer's instructions and [ESR-3997](#). Surfaces to be coated must be dry, clean and free of dirt, loose debris and other substances that could interfere with the adhesion of the coating. The coating is applied in one coat by airless spray equipment at ambient temperatures above 50°F (10°C) and relative humidity of less than 70 percent.

4.4 Ignition Barrier – Attics and Crawl Spaces:

4.4.1 Application with a Prescriptive Ignition Barrier: When North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation is installed within attics or crawl spaces where entry is made only for service of utilities, an ignition barrier must be installed in accordance with IBC Section 2603.4.1.6 and IRC Sections R316.5.3 and R316.5.4, as applicable. The ignition barrier must be consistent with the requirements for the type of construction required by the applicable code, and must be installed in a manner so that the foam plastic insulation is not exposed. The attic or crawl space area must be separated from the interior of the building by an approved 15-minute thermal barrier as described in Section 4.3.1.

North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation, as described in this section, may be installed in unvented attics in accordance with 2018, 2015 and 2012 IRC Section R806.5 (2009 IRC Section R806.4) or 2018 IBC Section 1202.3 (2015 IBC Section 1203.3).

4.4.2 Application without a Prescriptive Ignition Barrier: Where the spray-applied insulation is installed in accordance with Section 4.4.2.1, the following conditions apply:

- a) Entry to the attic or crawl space is to only service utilities, and no storage is permitted.
- b) There are no interconnected attic or crawl space areas.
- c) Air in the attic or crawl space is not circulated to other parts of the building.
- d) Attic ventilation is provided when required by 2018 IBC Section 1202.2 (2015, 2012 and 2009 IBC Section 1203.2) or IRC Section R806, except when air-impermeable insulation is permitted in unvented attics in accordance with the 2018 IBC Section 1202.3 (2015 IBC Section 1203.3) or 2018, 2015 and 2012 IRC Section R806.5 (2009 IRC Section R806.4). Under-floor (crawl space) ventilation is provided when required by 2018 IBC Section 1202.4 (2015 IBC Section 1203.4, 2012 and 2009 IBC Section 1203.3) or IRC Section R408.1, as applicable.
- e) Combustion air is provided in accordance with *International Mechanical Code*[®] Section 701.

4.4.2.1 Application without a Prescriptive Ignition Barrier: In attics and crawl spaces, North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation may be spray-applied to the underside of roof sheathing and/or rafters, and to vertical surfaces and the underside of floors as described in this section. The thickness of the foam plastic applied to the underside of the overhead surfaces (roof sheathing, rafters and the underside of floors) must not exceed 1 1/2 inches (292 mm). The thickness of the foam plastic applied to vertical surfaces must not exceed 7 1/2 inches (191 mm). The insulation may be left exposed without a prescriptive ignition barrier or fire-protective coating. The attic or crawl space must be separated from the interior of the building by an approved 15-minute thermal barrier as described in Section 4.3.1.

4.4.2.2 Use on Attic Floors: North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation may be installed at a maximum thickness of 1 1/2 inches (292 mm) between and over joists in attic floors. The North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be separated from the interior of the building by an approved thermal barrier. The coating specified in Section 4.3.2 and the ignition barrier in accordance with IBC Section 2603.4.1.6 and IRC Section R316.5.3 may be omitted.

4.5 Exterior Walls of Type I, II, III and IV Construction:

4.5.1 General: When used on exterior walls of Type I, II, III, and IV construction that are 40 feet (12 192 mm) or less above grade plane, the EPS 2000, Closed Cell, Spray Foam Insulation must comply with Section 2603.5 of the IBC and this section (Section 4.5). The insulation must not exceed a maximum thickness of 3.2 inches (81 mm). The potential heat of North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation is 1953 Btu/ft² (22.0 Mj/m²) per inch of thickness when tested in accordance with NFPA 259.

4.5.2 Specific Wall Assemblies: One layer of 5/8-inch-thick (15.9 mm), Type X gypsum wallboard complying with ASTM C36 or ASTM C1396 is installed with the long dimension perpendicular to 3 5/8-inch-deep (92 mm), No. 20 gage steel studs spaced a maximum of 24 inches (610 mm) on center. The wallboard is attached with No. 6, 1 1/4-inch-long (32 mm), self-tapping screws located 8 inches (203 mm) on center along the perimeter and in the field of the wallboard. Wallboard joints must be taped and treated with joint compound in accordance with ASTM C840 or GA-216. Fastener heads must also be treated with joint compound in accordance with ASTM C840 or GA-216.

4.5.3 Exterior Face: One layer of 5/8-inch-thick (15.9 mm) sheathing complying with ASTM C1177 is attached to steel studs using 1 1/4-inch-long (32 mm), self-tapping screws spaced 8 inches (203 mm) on center along the perimeter and in the field of the sheathing. EPS 2000, Closed Cell, Spray Foam Insulation spray-applied polyurethane foam insulation, at a maximum thickness of 3.2 inches (81 mm), is spray-applied onto the exterior of sheathing. Brick ties, 3 1/2 inches long (89 mm), must be installed at a nominal 24 inches on center to each vertical steel stud, using two No. 14 by 5-inch-long (127 mm) hex head screws. Exterior veneer must be 4-inch-thick (102 mm) standard brick with a nominally 2-inch air gap between brick and the foam plastic insulation.

5.0 CONDITIONS OF USE:

The North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions

- 5.1 This evaluation report and the manufacturer's published installation instructions, when required by the code official, must be submitted at the time of permit application.
- 5.2 North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation and applicable coating must be installed in accordance with the manufacturer's published installation instructions, this report and the applicable code. The instructions within this report govern if there are any conflicts between the manufacturer's published installation instructions and this report.
- 5.3 North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be separated from the interior of the building by an approved thermal barrier, as described in Section 4.3.1, except when installation is as described in Section 4.3.2 and 4.4.
- 5.4 North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be protected from the weather during application.
- 5.5 North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation must be applied by installers approved by North American Spray Foam Polymers.
- 5.6 Use of North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation in areas where the probability of termite infestation is "very heavy" must be in accordance with 2018, 2015 and 2009 IBC Section 2603.8 (2012 IBC Section 2603.9) or IRC Section R318.4, as applicable.
- 5.7 Jobsite certification and labeling of the insulation must comply with 2018 and 2015 IRC Sections N1101.10.1 and N1101.10.1.1, 2012 IRC Sections N1101.12.1 and N1101.12.1.1 or 2009 IRC Sections N1101.4 and N1101.4.1) and 2018, 2015 and 2012 IECC Sections C303.1.1, C303.1.1.1, R303.1.1 and R303.1.1.1 (2009 IECC Sections 303.1.1 and 303.1.1.1), as applicable.
- 5.8 When use is on exterior walls of buildings of Types I, II, III, and IV, construction must be as described in Section 4.5 and must not exceed 40 feet (12 192 mm) above grade plane.
- 5.9 North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation is produced in Arlington, Texas and Boisbriand, Quebec, Canada under a quality-control program with inspections by ICC-ES.

6.0 EVIDENCE SUBMITTED

- 6.1 Data in accordance with the [ICC-ES Acceptance Criteria for Spray-applied Foam Plastic Insulation \(AC377\)](#), dated April 2016, including reports of tests in accordance with Appendix X of AC377.
- 6.2 Reports on room corner tests in accordance with NFPA 286.
- 6.3 Report on air leakage testing in accordance with ASTM E283.
- 6.4 Reports on water vapor transmission tests in accordance with ASTM E96 (desiccant method).
- 6.5 Reports of fire propagation characteristics tests in accordance with NFPA 285.
- 6.6 Reports of potential heat of foam plastic tests in accordance with NFPA 259.
- 6.7 Supplementary fire engineering analysis.

7.0 IDENTIFICATION

- 7.1 Components for North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation are identified with the manufacturer's name (North American Spray Foam Polymers), address and telephone number; the product trade name (North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation); product type (A or B component); use instructions; the density; the flame-spread and smoke-developed indices; the evaluation report number (ESR-4484).

The TPR² Corporation Blazelok™ TBX coating is labeled with the manufacturer's name, the product trade name, date of manufacture, shelf life or expiration date, manufacturer's instructions for application and [ESR-3997](#).

The International Fireproof Technology / Paint To Protect, Inc. DC 315 coating is identified with the manufacturer's name, the product trade name, date of manufacture, shelf life or expiration date, manufacturer's instructions for application and ICC-ES evaluation report number [ESR-3702](#).

7.2 The report holder's contact information is the following:

NORTH AMERICAN SPRAY FOAM POLYMERS

7901 4TH STREET, SUITE 4021

ST. PETERSBURG, FLORIDA 33702

(800) 713-1646

www.northamericansprayfoam.com

8.0 OTHER CODES

8.1 Scope:

In addition to the codes referenced in Section 1.0, the products recognized in this report have also been evaluated for compliance with the following codes:

- 2006 IBC
- 2006 IRC
- 2006 IECC

8.2 Uses:

The products comply with the above-mentioned codes as described in Sections 2.0 through 7.0 of this report, except as noted below:

- **Application with a Prescriptive Thermal Barrier:** See Section 4.3.1, except the approved thermal barrier must be installed in accordance with Section R314.4 of the 2006 IRC.
- **Application without a Prescriptive Thermal Barrier:** See Section 4.3.2.
- **Application with a Prescriptive Ignition Barrier:** See Section 4.4.1, except attics must be vented in accordance with Section 1203.2 of the 2006 IBC or Section R806 of the 2006 IRC, and crawl space ventilation must be in accordance with 2006 IBC Section 1203.3 or 2006 IRC Section R408, as applicable.
- **Application without a Prescriptive Ignition Barrier:** See Section 4.4.2, except attics must be vented in accordance with Section 1203.2 of the 2006 IBC or Section R806 of the 2006 IRC, crawl space ventilation must be in accordance with 2006 IBC Section 1203.3 or 2006 IRC Section R408, as applicable, and combustion air is provided in accordance with 2006 *International Mechanical Code*[®] Sections 701 and 703.
- **Protection Against Termites:** See Section 5.6, except use of the insulation in areas where the probability of termite infestation is "very heavy" must be in accordance with Section R320.5 of the 2006 IRC.
- **Jobsite Certification and Labeling:** See Section 5.7, except jobsite certification and labeling must comply with Sections 102.1.1 and 102.1.1.1, as applicable, of the 2006 IECC.

TABLE 1—THERMAL RESISTANCE (R-VALUES)¹

THICKNESS (inches)	NORTH AMERICAN SPRAY FOAM POLYMERS EPS 2000, CLOSED CELL SPRAY POLYURETHANE FOAM INSULATION R-VALUE (°F.ft ² .h/Btu)
1	6.7
2	13
3	19
3.5	23
4	26
5	32
5.5	35
6	39
7	45
7.75	50
8	51
9	58
10	64
11	71
12	77
13	84
14	90
15	97
16	103

For **SI**: 1 inch = 25.4 mm; 1°F.ft².hr/Btu = 0.176 110 k.m²/W.

¹Calculated R-values are based on tested K-values at 1- and 3.5-inch thicknesses

*R-values greater than 10 are rounded to the nearest whole number

DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION

Section: 07 21 00—Thermal Insulation

REPORT HOLDER:

NORTH AMERICAN SPRAY FOAM POLYMERS

EVALUATION SUBJECT:

EPS 2000, CLOSED CELL, SPRAY FOAM INSULATION

1.0 REPORT PURPOSE AND SCOPE

Purpose:

The purpose of this evaluation report supplement is to indicate that North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation closed cell spray foam product, described in ICC-ES evaluation report ESR-4484 has also been evaluated for compliance with the codes noted below.

Applicable code editions:

- 2017 *Florida Building Code—Residential*
- 2017 *Florida Building Code—Building*

2.0 CONCLUSIONS

The North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation closed cell spray foam product, described in Sections 2.0 through 7.0 of the evaluation report ESR-4484, complies with the *Florida Building Code—Residential* and *Florida Building Code—Building*, provided the design and installation are in accordance with the 2012 *International Building Code*® (IBC) provisions noted in the evaluation report.

Installation must meet the requirements of Sections 1403.8 and 2603.8 of the *Florida Building Code—Building* and Sections R318.7 and R318.8 of the *Florida Building Code—Residential*, as applicable.

Use of the North American Spray Foam Polymers EPS 2000, Closed Cell, Spray Foam Insulation closed cell spray foam product for compliance with the High-Velocity Hurricane Zone provisions of the *Florida Building Code—Residential* and *Florida Building Code—Building* has not been evaluated, and is outside the scope of this supplemental report.

For products falling under Florida Rule 9N-3, verification that the report holder's quality assurance program is audited by a quality assurance entity approved by the Florida Building Commission for the type of inspections being conducted is the responsibility of an approved validation entity (or the code official when the report holder does not possess an approval by the Commission).

This supplement expires concurrently with the evaluation report, reissued September 2024.