

ICC Design No. IFRM-1191-02

ESL-1191

Issued November 2019 Revised June 11, 2021

This listing is subject to renewal November 2021.

www.icc-es.org | (800) 423-6587 | (562) 699-0543

A Subsidiary of the International Code Council®


Applicant: FLAMEOFF COATINGS, INC.

Product: FLAMEOFF® FIRE BARRIER PAINT

Standard: ASTM E119 (UL 263) / CAN/ULC-S101

Structural

Shape: H-sections or I-sections





COMPONENTS OF CONSTRUCTION:

- Structural Steel Column Wide flange steel columns (H-section or I-section) with Hp/A or W/D section factors based on exposure on four sides. Columns shall be free of dirt, loose scale, and oil before application of metal alkyd primer.
- 2. **Primer Coating** Structural steel to be primed with a layer of an alkyd metal primer with an average applied dry film thickness of 3.7 mils (0.09 mm). Primed surface should be cleaned, dried, and free of dirt, loose scale, grease, oil, and any contaminant that would inhibit bonding of the FlameOff® Barrier Paint to the primer.
- 3. FlameOff® Fire Barrier Paint Coating applied in accordance with manufacturer's instructions to the minimum dry film thicknesses shown in Table IFRM-1191-02, based on the column section factor and fire resistance period. Coating thicknesses may be interpolated between section factors at the same fire resistance period. Extrapolation beyond the minimum and maximum section factors and fire resistance periods is not permitted.

Table IFRM-1191-02 – H-section or I-section							
Secti	on Factor	Fire Resistance Period (min)					
Hp/A	W/D	60		90		120	
(m ⁻¹)	(lbs./in)	Thickness in mm (mils)					
70	1.91	0.8	(33)	1.5	(58)	2.3	(89)
80	1.67	0.8	(33)	1.5	(58)	2.5	(97)
90	1.49	0.8	(33)	1.6	(65)	2.7	(106)
100	1.34	0.8	(33)	1.8	(71)	2.9	(114)
110	1.22	0.9	(36)	2.0	(78)	3.1	(123)
120	1.12	1.0	(40)	2.1	(84)	3.3	(131)
130	1.03	1.1	(44)	2.3	(90)	3.5	(139)
140	0.96	1.2	(47)	2.4	(96)	3.8	(148)
150	0.89	1.3	(51)	2.6	(101)	4.0	(156)
160	0.84	1.4	(55)	2.7	(108)	4.2	(166)
162	0.83	1.4	(55)	2.7	(108)	4.2	(166)
170	0.79	1.5	(58)	2.9	(113)	-	(-)
180	0.74	1.6	(62)	3.0	(118)	-	(-)
190	0.71	1.7	(65)	3.1	(123)	-	(-)
200	0.67	1.7	(69)	3.3	(128)	-	(-)
210	0.64	1.8	(72)	3.4	(134)	-	(-)
220	0.61	1.9	(76)	3.5	(139)	-	(-)
230	0.58	2.0	(80)	3.6	(143)	-	(-)
240	0.56	2.1	(83)	3.8	(148)	-	(-)
250	0.54	2.2	(87)	3.9	(153)	-	(-)
260	0.52	2.3	(90)	4.0	(158)	-	(-)
270	0.50	2.4	(94)	4.1	(162)	-	(-)
280	0.48	2.5	(98)	-	(-)	-	(-)
290	0.46	2.6	(101)	-	(-)	-	(-)
300	0.45	2.7	(105)	-	(-)	-	(-)
306	0.44	2.7	(107)	-	(-)	-	(-)

For **SI**: 1 inch = 25.4 mm

Footnote: Empty cells ("-") indicate unknown performance of coating thickness.