

## ICC Design No. IFRM-1191-04

**ESL-1191**

Reissued November 2022

This listing is subject to renewal November 2023.

[www.icc-es.org](http://www.icc-es.org) | (800) 423-6587 | (562) 699-0543

A Subsidiary of the International Code Council®

**Applicant:** FLAMEOFF COATINGS, INC.


**Product:** FLAMEOFF® FIRE BARRIER PAINT

**Standard:** ASTM E119 (UL 263) / CAN/ULC-S101

**Structural**

**Shape:** W-Shape (H-section or I-section) Beams

*IFRM = Intumescent Fire-Resistive Materials*



Listings are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the listing or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this listing, or as to any product covered by the listing.

Copyright © 2022 ICC Evaluation Service, LLC. All rights reserved.

**COMPONENTS OF CONSTRUCTION:**

1. **Structural Steel Beams** – Wide flange steel beams (H-section or I-section) with  $H_p/A$  or  $W/D$  section factors based on exposure on three sides. Beams shall be free of dirt, loose scale, and oil before application of metal alkylid primer.
2. **Primer Coating** – Structural steel to be primed with a layer of an alkylid metal primer with an average applied dry film thickness of 3.1 mils (0.08 mm). Primed surface shall be cleaned, dried, and free of dirt, loose scale, grease, oil, and any contaminant that would inhibit bonding of the FlameOff® Barrier Paint to the primer.
3. **FlameOff® Fire Barrier Paint** – Coating applied in accordance with manufacturer's instructions to the minimum dry film thicknesses shown in IFRM-1191-04 Tables 1 and 2 based on the beam section factor (exposure on three sides) and fire resistance period. Coating thicknesses may be interpolated between section factors at the same fire resistance period. Extrapolation beyond the minimum and maximum section factors and fire resistance periods is not permitted.
4. **Concrete** – Minimum thickness over the steel deck and form unit crests must be 2½-inch-thick (63.5 mm) and have a minimum 3,000 psi (20.7 MPa) compressive strength and unit weight of  $145 \pm 3$  pcf ( $2323 \pm 48$  kg/m<sup>3</sup>).
5. **Steel Deck or Floor Units** – Minimum 2-inch (50.8 mm) deep galvanized fluted units with a nominal thickness of 0.039-inch (0.99 mm); welded to the structural steel beam.
6. **Shear Stud Connectors (Not Shown)** – (Optional) Headed type or equivalent per AISC Specification. Connectors must be welded to the top flange of the structural steel beam through the steel decking. Studs shall be designed and installed in accordance with AISC guidelines to provide composite action (between structural steel beam and concrete deck), as required.
7. **Mineral Wool Insulation (Not Shown)** – Flute spaces between the structural steel beam and the steel deck shall be completely filled with mineral wool insulation having a minimum density of 6.15 pcf (98.5 kg/m<sup>3</sup>).

**IFRM-1191-04 TABLE 1 – MINIMUM COATING THICKNESS FOR A W-SHAPE (H- OR I-SECTION) BEAM SECTION FACTOR TO ACHIEVE ESTIMATED FIRE RESISTANCE PERIOD (UNRESTRAINED BEAM RATING).**

Section Factor		Unrestrained Beam Rating			
Hp/A (m <sup>-1</sup> )	W/D (lbs./in)	Fire Resistance Period (min)			
		60		90	
		Thickness in mm (mils)			
70	1.91	1.19	(46.8)	1.84	(72.5)
80	1.67	1.19	(46.8)	1.84	(72.5)
90	1.49	1.19	(46.8)	1.84	(72.5)
100	1.34	1.25	(49.3)	1.95	(76.7)
110	1.22	1.31	(51.7)	2.05	(80.8)
120	1.12	1.37	(54.1)	2.16	(84.9)
130	1.03	1.44	(56.5)	2.26	(89.0)
140	0.96	1.50	(58.9)	2.37	(93.1)
150	0.89	1.56	(61.3)	2.47	(97.2)
160	0.84	1.62	(63.7)	2.57	(101.3)
168	0.80	1.67	(65.7)	2.66	(104.6)
170	0.79	1.68	(66.2)	2.68	(105.5)
180	0.74	1.74	(68.6)	2.78	(109.6)
190	0.71	1.80	(71.0)	2.89	(113.7)
194	0.69	1.83	(72.0)	2.93	(115.3)
200	0.67	1.86	(73.4)	-	( - )
210	0.64	1.93	(75.8)	-	( - )
220	0.61	1.99	(78.2)	-	( - )
230	0.58	2.05	(80.7)	-	( - )
240	0.56	2.11	(83.1)	-	( - )
250	0.54	2.17	(85.5)	-	( - )

For SI: 1 inch = 25.4 mm, 1 inch = 1000 mils

**IFRM-1191-04 TABLE 2 – MINIMUM COATING THICKNESS FOR A W-SHAPE (H- OR I-SECTION) BEAM SECTION FACTOR TO ACHIEVE ESTIMATED FIRE RESISTANCE PERIOD (RESTRAINED BEAM RATING).**

		Restrained Beam Rating					
Section Factor		Fire Resistance Period (min)					
Hp/A (m <sup>-1</sup> )	W/D (lbs./in)	60		90		120	
		Thickness in mm (mils)					
70	1.91	0.97	(38.2)	1.36	(53.6)	2.32	(91.2)
80	1.67	0.97	(38.2)	1.36	(53.6)	2.32	(91.2)
90	1.49	0.97	(38.2)	1.36	(53.6)	2.32	(91.2)
100	1.34	1.03	(40.6)	1.42	(56.0)	2.38	(93.6)
110	1.22	1.09	(43.0)	1.48	(58.5)	2.44	(96.0)
120	1.12	1.15	(45.5)	1.55	(60.9)	2.50	(98.4)
130	1.03	1.22	(47.9)	1.61	(63.3)	2.56	(100.8)
140	0.96	1.28	(50.3)	1.67	(65.7)	2.62	(103.2)
150	0.89	1.34	(52.7)	1.73	(68.1)	2.68	(105.7)
160	0.84	1.40	(55.1)	1.79	(70.5)	2.74	(108.1)
168	0.80	1.45	(57.1)	1.84	(72.5)	2.79	(110.0)
170	0.79	1.46	(57.5)	1.85	(72.9)	-	( - )
180	0.74	1.52	(60.0)	1.91	(75.4)	-	( - )
190	0.71	1.58	(62.4)	1.98	(77.8)	-	( - )
194	0.69	1.61	(63.3)	2.00	(78.7)	-	( - )
200	0.67	1.65	(64.8)	-	( - )	-	( - )
210	0.64	1.71	(67.2)	-	( - )	-	( - )
220	0.61	1.77	(69.6)	-	( - )	-	( - )
230	0.58	1.83	(72.0)	-	( - )	-	( - )
240	0.56	1.89	(74.4)	-	( - )	-	( - )
250	0.54	1.95	(76.9)	-	( - )	-	( - )

For **SI**: 1 inch = 25.4 mm, 1 inch = 1000 mils

Footnote: Empty cells (" - ") indicate unknown performance of coating thickness.